



akrylmetal
BY SYNPO

LV PL 370

Two-Component PUR Acrylic Filler for Plastics

Usage	Undercoat layer intended for sanding; contains special additives improving adhesion to plastics				
Color shades	Yellow, white, gray, red, green				
VOC g/l (Contents of organic solvents in mixed coating)	< 440 (Category – B/c)				
Substrate	Perfectly cleaned and degreased surfaces				
Hardening	4 : 1 parts by volume; or 5:1 weight parts Hardener LV BU 45 N				
Thinning	0 – 10 % b. v. Thinner LV PC 342				
Consistence of mixed coating	22 ¹⁾ – 45 ²⁾ s/4mm at 20 °C				
Coverage of mixed coating	6 - 8 m ² /l				
Application	HVLP ¹⁾ , AIRLESS ²⁾				
Number of sprays	2, flash time between layers 20 min at 20 °C				
Recommended thickness	60 - 80 µm				
Pot life of mixed coating	4 hours at 20 °C				
Drying	Dry-to-sand - 12 hrs at 20 °C, 60 min at 60 °C				
Product density g/m ³	Content of organic solvents kg/kg	Content of total organic carbon kg/kg	Content of non-volatile compounds – solids % b. v.	Solids volume in application mixture % b. v.	Content of heavy metals
1.25	0.35	0.3	50	45	neobsahuje
Caution	When handling the product follow all safety precautions indicated in the Material Safety Data Sheet and the label. Flammable liquid, Hazard Class II. Contains organic solvents. Store in a dry place at temperatures from 10 °C to 25 °C.				

SYNPO, akciová společnost
S. K. Neumanna 1316, 532 07 Pardubice, Czech Republic
Tel: +420466 067 250 Fax: +420 466 067 260
e-mail: akrylmetal@synpo.cz

Valid from February 2015